



Material - EN 1.4950

Standard Specification for Steels for Pressure Purposes; Austenitic Steels

Group - Ferrous Stainless Steel Alloys

Sub Group - EN 1.4950 Steels for Pressure Purposes; Austenitic Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Flat Products Made of Steels for Pressure Purposes

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.080	Annealing	
Silicon	Si %	0.700 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	12.000 - 15.000		
Nitrogen	N %	0.100 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 510 - 730 Yield Strength in Mpa 200 min. Elongation in % 35 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 60 @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-351 Grade CH10	ASME	USA	Casting
J93401	UNS	USA	Casting
309S	AISI	USA	Casting
SUS 309 STB	JIS	Japan	Superheater, Tubes of Boiler and Heat Exchangers
X 6 CrNi 23-14	UNI	Italy	Plate, Sheets, Strip and Coil
A743 CH10	ASTM	USA	Casting
A351 CH10	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.