



Material - EN 1.4982

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - EN 1.4982 Seemless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.150		
Silicon	Si %	0.200 - 1.000		
Manganese	Mn %	5.500 -7.000	Solution Annealing	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	14.000 - 16.000		
Molybdenum	Mo %	0.800 - 1.200		
Nickel	Ni %	9.000 - 11.000		-
Niobium	Nb %	0.750 - 1.250	Mechanical Properties	
Vanadium	V %	0.150 - 0.400	Tensile Strength in Mpa	540 - 850
Boron	В %	0.003 - 0.009	Yield Strength in Mpa	220 min.
Iron	Fe %	Balance	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	50 J @ RT

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
10216-5 EN 1.4982	BS	British	Tube		
1.4982	DIN	Germany	Steel		
X10CrNiMoMnNbVB15101	EN	European Union	Steel and Tube		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.