



Material - EN 1.7383

EN 10222-2 Steel forgings for pressure purposes

Group - Ferrous Mild Steel Alloys

Sub Group - EN 10222-2 Steel forgings for pressure purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.150	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.400 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.100		
Nickel	Ni %	0.300 max.		
Vanadium	V %	0.020 max.	Mechanical Properties	
Niobium	Nb %	0.010 max.	Tensile Strength in Mpa	450 - 600
Copper	Cu %	0.300 max.	Yield Strength in Mpa	255 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	34 min.

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
J22090	UNS	USA	Casting	
1.7379	DIN	Germany	Forging	
10 CD 9.10	AFNOR NF	France	Forging	
622	BS	British	Bar	
GS 18 CrMo 9 10	ONORM	Australia	Steel	
8 CrMoNiNb 9-10	DIN	Germany	Steel	
A757 D1N1 D1Q1	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.