



Material - EN 1.8932

Standard Specification for Steel Forgings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - EN 1.8932 Steel Forgings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.600 Max.		
Manganese	Mn %	1.100 - 1.700		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	0.030 max.		
Nickel	Ni %	0.800 max.		
Molybdenum	Mo %	0.010 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.200 max.		
Niobium	Nb %	0.050 max.	Mechanical Properties	
Aluminium	Al %	0.020 Min.	Tensile Strength in Mpa	490 - 690
Nitrogen	N %	0.020 max.	Yield Strength in Mpa	340 min.
Iron	Fe %	Balance	Elongation in %	19 min.
-	-	-	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-487 Garde 16A	ASME	USA	Casting
1.6222	DIN	Germany	Steel
J31200	UNS	USA	Casting
E 460 DD	JIS	Japan	Plate
P 420 NH	EN	European Union	Forging
9 NiMn 5	DIN	Germany	Steel
A487 16A	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.