



## Material - EN 10083-3 1.6773

### Standard Specification for Mild Steel Alloys Bar and Rod

Group - Ferrous Mild Steel Alloys

Sub Group - EN 10083-3 1.6773 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.390	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	1.600 - 2.000		
Molybdenum	Mo %	0.250 - 0.450		
Nickel	Ni %	3.600 - 4.100		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa   1000 - 1200 Yield Strength in Mpa   800 min. Elongation in %   11 min. Reduction of Area in %   - Hardness in BHN   As Per HT Impact in Joule   45 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
35NiCrMo16	EN	European Union	Bar and Rod
35 NCD 16	AFNOR NF	France	Bar, Wire and Rod
835 M 30	BS	British	Bar and Rod
SFNCM 1030 R	JIS	Japan	Forging
SFNCM 830 R	JIS	Japan	Forging
SFNCM 880 R	JIS	Japan	Forging
SFNCM 930 R	JIS	Japan	Forging

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.