

Material - EN 10083-3 1.7003

Standard Specification for Mild Steel Alloys Bar and Rod

Group - Ferrous Mild Steel Alloys

Sub Group - EN 10083-3 1.7003 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition		Heat Treatment	
C %	0.350 - 0.420	As Raw or Annealing or Normalizing or Hardening and Tempering	
Si %	0.400 max.		
Mn %	0.500 - 0.800		lizing or Llordoning and
Р%	0.025 max.		•
S %	0.035 max.		
Cr %	0.400 - 0.600		
Fe %	Balance		
-	-		
-	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	600 - 750
-	-	Yield Strength in Mpa	350 min.
-	-	Elongation in %	17 - 45
-	-	Reduction of Area in %	-
-	-	Hardness in BHN	As Per HT
-	-	Impac <mark>t in Joule</mark>	35 J @ RT
	C % Si % Mn % P % S % Cr % Fe % - - - - - - - - - - - - - - - - - - -	C % 0.350 - 0.420 Si % 0.400 max. Mn % 0.500 - 0.800 P % 0.025 max. S % 0.035 max. Cr % 0.400 - 0.600 Fe % Balance - - - - - - - - - - - - - - - - - - - - - - - - - -	C % 0.350 - 0.420 Si % 0.400 max. Mn % 0.500 - 0.800 P % 0.025 max. S % 0.035 max. Cr % 0.400 - 0.600 Fe % Balance - - <t< td=""></t<>

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
38Cr2	EN	European Union	Bar and Rod	
1.7023	ONORM	Australia	Bar and Rod	
38 CrS 2	ONORM	Australia	Bar and Rod	
38 CrS 2	EN	European Union	Bar and Rod	
1.7023	EN	European Union	Bar and Rod	
38 CrS 2	SFS	Finland	Bar and Rod	
1.7023	SFS	Finland	Bar and Rod	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS