

Material - EN 10083-3 20MnB5

Standard Specification for Mild Steel Alloys Bar and Rod

Group - Ferrous Mild Steel Alloys

Sub Group - EN 10083-3 20MnB5 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition		Heat Treatment	
C %	0.170 - 0.230	As Raw or Annealing or Normalizing or Hardening and Tempering	
Si %	0.400 max.		
Mn %	1.100 - 1.400		lizing or Hardoning and
Р%	0.025 max.		č
S %	0.035 max.		
В%	0.0008 - 0.0050		
Fe %	Balance		
-	-		
-	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	750 - 900
-	-	Yield Strength in Mpa	600 min.
-	-	Elongation in %	15 min.
-	-	Reduction of Area in %	-
-	-	Hardn <mark>ess in BH</mark> N	As Per HT
-	-	Impac <mark>t in Joule</mark>	60 J @ RT
	C % Si % Mn % P % S % B % Fe % - - - - - - - - - - - - - - - - - - -	C % 0.170 - 0.230 Si % 0.400 max. Mn % 1.100 - 1.400 P % 0.025 max. S % 0.035 max. B % 0.0008 - 0.0050 Fe % Balance - - - - - - - - - - - - - - - - - - - - - - - - - -	C % 0.170 - 0.230 Si % 0.400 max. Mn % 1.100 - 1.400 P % 0.025 max. S % 0.035 max. B % 0.0008 - 0.0050 Fe % Balance - - <

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.5530	EN	European Union	Bar and Rod
20 MB 5	AFNOR NF	France	Bar, Wire and Rod
20MnB5	ISO	International	Bar and Rod
1.553	UNI	Italy	Steel and Strip
20MnB5	UNI	Italy	Steel and Strip
1.553	BS	British	Steel and Strip
20MnB5	BS	British	Steel and Strip

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS