



## Material - EN 10083-3 34CrMo4

## Standard Specification for Mild Steel Alloys Bar and Rod

**Group - Ferrous Mild Steel Alloys** 

Sub Group - EN 10083-3 34CrMo4 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.370	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 0.900		alizing or Hardoning and
Phosphorus	P %	0.025 max.		· ·
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.900 - 1.200		
Molybdenum	Mo %	0.150 - 0.300		
Iron	Fe %	Balance		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	700 - 850
-	-	-	Yield Strength in Mpa	450 min.
-	-	-	Elongation in %	15 - 60
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	As Per HT
-	-	-	Impac <mark>t in Joule</mark>	45 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.7220	EN	European Union	Bar and Rod	
34CrMoS4	EN	European Union	Bar and Rod	
1.7226	EN	European Union	Bar and Rod	
P 880 - 34CrMo4	AFNOR NF	France	Bar and Rod	
CMo 3 Z	MSZ	Hungary	Bar and Rod	
34 CrMo 4 E	ISO	International	Bar and Rod	
34 CrMo 4 E	JIS	Japan	Bar and Rod	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.