



## Material - EN 5.3104

## **Standard Specification For Spheoidal Graphiite Cast Irons Castings**

Group - Ferrous SG Iron I Ductile Iron Alloys
Sub Group - EN 5.3104 Spheoidal Graphiite Cast Irons Castings
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	-		
Silicon	Si %	-		
Manganese	Mn %	-	As-Cast	
Phosphorus	Р%	-		
Sulphur	S %	-		
Chromium	Cr %	-		
Nickel	Ni %	-		
Copper	Cu %	-		_
Iron	Fe %	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	350 min.
-	-	-	Yield Strength in Mpa	230 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	12 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
JS 400-18-RT	ISO	International	Casting	
JS 400-18-RT	AS	Australia	Casting	
EN-GJS-400-18-RT	AFNOR NF	France	Casting	
EN-JS1024	DIN	Germany	Casting	
EN-GJS-400-18-RT	UNI	Italy	Casting	
EN-GJS-400-18-RT	NS	Norway	Casting	
EN-JS1024	BS	British	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.