



## Material - EN G 19 NiCrMo 12 6

### Standard Specification for Heat treatable alloyed NiCrMo steel

Group - Ferrous Mild Steel Alloys

Sub Group - EN G 19 NiCrMo 12 6 Heat treatable alloyed NiCrMo steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	1.350 - 1.850		
Molybdenum	Mo %	0.350 - 0.600		
Nickel	Ni %	2.500 - 3.500		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	450 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	41 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.6783	EN	European Union	Casting
1.6783	DIN	Germany	Casting
UNS J42220	UNS	USA	Casting
G19 NiCrMo 12-6	DIN	Germany	Casting
A757 Grade E1Q	ASTM	USA	Casting
A757 Grade E2N1, E2Q1	ASTM	USA	Casting
A757 Grade E2N1, E2Q2	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.