



Material - EN X 6 CrNiTiB 18-10

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - EN X 6 CrNiTiB 18-10 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel and Flat

Chemical			
Carbon	C %	0.040 - 0.080	
Silicon	Si %	1.000 max.	
Manganese	Mn %	2.000 max.	
Phosphorus	P %	0.035 max.	
Sulphur	S %	0.015 max.	
Chromium	Cr %	17.000 - 19.000	
Nickel	Ni %	9.000 - 12.000	
Titanium	Ti %	0.800 max.	
Boron	В %	0.0015 - 0.0050	
Iron	Fe %	Balance	Tensile S
-	-	-	Yield St

Solution Annealing	

Mechanical Pr	operties	
Tensile Strength in Mpa	490 - 710	
Yield Strength in Mpa 210 min.		
Elongation in %	30 min.	
Reduction of Area in %	-	
Hardness in BHN	-	
Impac <mark>t in Joule</mark>	60 J @ RT	

Heat Treatment

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
10216-5 EN 1.4941	BS	British	Tube		
1.4941	DIN	Germany	Steel and Flat		
1.4941	EN	European Union	Steel and Flat		
Z6 CNT 18-10B	AFNOR NF	France	Steel		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.