

## Material - EN X 6 NiCrSiNCe 35 25

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - EN X 6 NiCrSiNCe 35 25 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.080		
Silicon	Si %	1.200 - 2.000		
Manganese	Mn %	2.000 max.	Solution Annealing	
Phosphorus	Р%	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	34.000 - 36.000		
Nitrogen	N %	0.120 - 0.200		
Cerium	Ce %	0.030 - 0.080	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	650 - 850
-	-	-	Yield Strength in Mpa	300 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	210 max.
-	-	-	Impac <mark>t in Joule</mark>	-
		-		

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S35315	ASTM	USA	Steel, Plate, Sheet and Strip	
S35315	UNS	USA	Steel	
A167 S35315	ASTM	USA	Steel, Sheet, Plate and Strip	
A312 S35315	ASTM	USA	Steel and Pipe	
A959 S35315	ASTM	USA	Steel	
SA-240 UNS S35135	ASME	USA	Steel	
SA-312 UNS S35135	ASME	USA	Steel and Pipe	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS