



## Material - GOST 15ch13L

### Standard Specification for Steel Castings Suitable for Pressure Service

Group - Ferrous Stainless Steel Alloys

Sub Group - GOST 15ch13L Steel Castings Suitable for Pressure Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.200 - 0.800		
Manganese	Mn %	0.300 - 0.800		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	12.000 - 14.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	600 - 800
-	-	-	Yield Strength in Mpa	420 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
410.0000	AISI	USA	Bar, Wire, Shapes and Forging
410 C 21	BS	British	Casting
5351	AMS	USA	Casting
385 G X 12 Cr 13	SFS	Finland	Casting
A217 CA 15	ASTM	USA	Casting
A487 CA 15	ASTM	USA	Casting
A743 CA 15	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.