GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - Gravity 08H14F

Standard Specification for Stainless and Heat Resisting Steels

Group - Ferrous Stainless Steel Alloys

Sub Group - Gravity 08H14F Stainless and Heat Resisting Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel, Bars, Rods, Casting and Forging

Chemical Composition		
Carbon	C %	0.030 - 0.100
Silicon	Si %	1.000 max.
Manganese	Mn %	0.800 - 1.200
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	13.000 - 15.500
Nickel	Ni %	1.000 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or As-Cast or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	600 min.
Yield Strength in Mpa	400 min.
Elongation in %	10 min.
Reduction of Area in %	20 min.
Hardness in HB	200 - 300
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
36016-1 F.3422	UNE	Spain	Steel
36016-2 F.3424	UNE	Spain	Steel
36016-2 X 55 CrMoV 14	UNE	Spain	Steel
36016-1 X 45 CrMoV 14	UNE	Spain	Steel
3583 45 VMoCr 145	STAS	Romania	Steel
EN 10088-3 1.4116	DIN	Germany	Steel
EN 10088-2 X50CrMoV15	DIN	Germany	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.