GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - Gravity 11RM20

Standard Specification for Stainless and Heat Resisting Steels

Group - Ferrous Stainless Steel Alloys

Sub Group - Gravity 11RM20 Stainless and Heat Resisting Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel, Bars, Rods, Casting and Forging

Chemical Composition		
Carbon	C %	0.090 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	4.500 - 6.500
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	16.000 - 18.000
Nickel	Ni %	4.000 - 6.000
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or As-Cast or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	400 min.
Yield Strength in Mpa	200 min.
Elongation in %	25 min.
Reduction of Area in %	40 min.
Hardness in HB	130 - 230
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 35-573 Z 12 CMN 17-07 Az	AFNOR NF	France	Steel
683-13 A-2	ISO	International	Steel
G 4309 SUS 201	JIS	Japan	Steel and Wire
EN 10088-2 X 12 CrMnNiN 17-7-5	UNI	Italy	Casting
EN 10088-1 1.4372	DIN	Germany	Steel
10088-1 X 12 CrMnNiN 17 7 5	EN	European Union	Steel
10088-1 1.4372	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.