GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - Gravity 13G1SU Coils

Standard Specification for Structural and Constructional Steels

Group - Ferrous Mild Steel Alloys

Sub Group - Gravity 13G1SU Coils Structural and Constructional Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel, Bars, Rods, Casting and Forging

Chemical Composition		
Carbon	C %	0.100 - 0.160
Silicon	Si %	0.600 max.
Manganese	Mn %	1.250 - 1.550
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	0.030 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or As-Cast or Annealing or Normalizing or Normalizing & Tempering or Quenching & Tempering or Hardening & Tempering

Mechanical Properties	
Tensile Strength in Mpa	350 min.
Yield Strength in Mpa	180 min.
Elongation in %	20 min.
Reduction of Area in %	35 min.
Hardness in HB	100 - 200
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
4360 40 DD	B.S.	United Kingdom	Steel
A 35-501 E 28-3	AFNOR NF	France	Steel
17162-2 St E350-3Z	DIN	Germany	Strip and Sheet
17162-2 1.0529	DIN	Germany	Strip and Sheet
5952 HAS 365W	ISO	International	Steel and Sheet
D 3529 HSA 365W	KS	Korea	Steel
G 3126 SLA 365	JIS	Japan	Steel and Plates

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.