GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - Gravity 17GS

Standard Specification for Structural and Constructional Steels

Group - Ferrous Mild Steel Alloys

Sub Group - Gravity 17GS Structural and Constructional Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel, Bars, Rods, Casting and Forging

Chemical Composition		
Carbon	C %	0.150 - 0.200
Silicon	Si %	0.600 max.
Manganese	Mn %	1.100 - 1.400
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	0.300 max.
Nickel	Ni %	0.300 max.
Copper	Cu %	0.300 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or As-Cast or Annealing or Normalizing or Normalizing & Tempering or Quenching & Tempering or Hardening & Tempering

Mechanical Properties	
Tensile Strength in Mpa	350 min.
Yield Strength in Mpa	180 min.
Elongation in %	20 min.
Reduction of Area in %	35 min.
Hardness in HB	100 - 200
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K02011	UNS	USA	Steel
6280 45 B	MSZ	Hungary	Steel
365 (G-20 Mn 5)	SFS	Finland	Casting
A 738 Grade C	ASTM	USA	Steel and Plates
A 333 Grade 10	ASTM	USA	Steel and Pipe
84023/05 16 G 2	PN	Poland	Steel
84023/08 18 G 2 AA	PN	Poland	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.