GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - Gravity 214MN

Standard Specification for Stainless and Heat Resisting Steels

Group - Ferrous Stainless Steel Alloys

Sub Group - Gravity 214MN Stainless and Heat Resisting Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel, Bars, Rods, Casting and Forging

Chemical Composition		
Carbon	C %	0.480 - 0.580
Silicon	Si %	1.500 max.
Manganese	Mn %	8.000 - 10.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	20.000 - 22.000
Nickel	Ni %	3.000 - 5.000
Nitrogen	N %	0.300 - 0.500
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or As-Cast or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	400 max.
Yield Strength in Mpa	200 min.
Elongation in %	25 min.
Reduction of Area in %	40 min.
Hardness in HB	130 - 230
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
10090 1.4871	EN	European Union	Steel
EN 10090 1.4871	DIN	Germany	Steel
17480 1.4871	DIN	Germany	Steel
970-4 349 S 52	B.S.	United Kingdom	Steel
5632 55Ch20G9AN4	GOST	Russia	Steel
J 775 EV 8	SAE	USA	Steel
5776 SZ 13	MSZ	Hungary	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.