

## Material - IS 10774 Grade 7

Standard Specification for Corrosion Resistant High Alloy Steel and Nickel Base Castings for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - IS 10774 Corrosion Resistant High Alloy Steel and Nickel Base Castings for General Applications Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.		
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	Annealing or Hardening + Tempering	
Sulphur	S %	0.040 max.		
Chromium	Cr %	11.500 - 14.000		
Molybdenum	Mo %	0.500 max.		
Nickel	Ni %	1.000 max.		_
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	450 min.
-	-	-	Elongation in %	16 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	241 max.
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A217 CA 15	ASTM	USA	Casting	
A487 CA 15	ASTM	USA	Casting	
5351	AMS	USA	Casting	
410	AISI	USA	Bar, Wire, Shape and Forging	
410 C 21	BS	British	Casting	
15Ch13L	GOST	Russia	Casting	
385 G X 12 Cr 13	SFS	Finland	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.