GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 3038 Grade 6

Standard Specification for Martensitic Stainless Steel and Alloy Steel Castings for Pressure Containing Parts Suitable for High Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - IS 3038 Grade 6 Martensitic Stainless Steel and Alloy Steel Castings for Pressure Containing Parts Suitable for High Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Carbon	C %	0.200 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	0.400 - 0.700
Sulphur	S %	0.045 max.
Phosphorus	P %	0.040 max.
Chromium	Cr %	4.000 - 6.500
Nickel	Ni %	0.500 max.
Molybdenum	Mo %	0.450 - 0.650
Vanadium	V %	0.050 max.
Copper	Cu %	0.500 max.
Tungsten	W %	0.100 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment
As-Cast or Normalizing + Tempering

Mechanical Properties	
Tensile Strength in Mpa	620 - 795
Yield Strength in Mpa	415 min.
Elongation in %	17 min.
Reduction of Area in %	35 min.
Hardness in HV	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J42045	UNS	USA	Steel and Casting
2074 L5E	AS	Australia	Steel and Casting
3606 625	B.S.	United Kingdom	Steel and Tubing
3604-1 625	B.S.	United Kingdom	Steel and Tubing
1504 625	B.S.	United Kingdom	Steel and Casting
3100 B 5	B.S.	United Kingdom	Steel and Casting
A 217 Grade C5	ASTM	USA	Steel and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.