

Material - IS 3444 Grade 9

Standard Specification for Corrosion Resistant High Alloy Steel and Nickel Base Castings for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - IS 3444 Corrosion Resistant High Alloy Steel and Nickel Base Castings for General Applications Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Solution Annealing	
Silicon	Si %	2.000 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	26.000 - 30.000		
Nickel	Ni %	8.000 - 11.000		
Iron	Fe %	Balance		-
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	09 min.
-	-		Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
J93423	UNS	USA	Casting	
A 743 CE30	ASTM	USA	Casting	
A451 Grade CPH20	ASTM	USA	Casting	
SA-451 Grade CPH20	ASME	USA	Casting	
CH-20	NBR	Brazil	Casting	
CH-20	NMX	Maxico	Casting	
13505 Grade 4	IS	India	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.