GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 4367 55Si7

Standard Specification for Alloy Steel Forgings for General Industrial Use

Group - Ferrous Mild Steel Alloys

Sub Group - IS 4367 55Si7 Alloy Steel Forgings for General Industrial Use

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Forging

Chemical Composition		
Carbon	C %	0.500 - 0.600
Silicon	Si %	1.500 - 2.000
Manganese	Mn %	0.800 - 1.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	1300 - 1500
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
IS 4368 55Si2Mn90	IS	India	Billets, Blooms and Slabs
IS 2507 55Si7	IS	India	Steel and Strip
IS 1570 55Si7	IS	India	Steel
17221 38 Si 7	DIN	Germany	Steel
EU 89 45 Si 7	EN	European Union	Steel
35-571 40 Si 7	AFNOR NF	France	Steel
37-504 45 S 7	AFNOR NF	France	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.