



## Material - IS 4522 Grade 13

## Standard Specification for Heat Resistant Alloy Steel and Nickel Base Castings

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - IS 4522 Grade 13 Heat Resistant Alloy Steel and Nickel Base Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition		Heat Treatment	
C %	0.350 - 0.750		
Si %	2.500 max.		
Mn %	2.000 max.	As - Cast or Annealing	
P %	0.050 max.		
S %	0.050 max.		
Cr %	17.000 - 21.000		
Ni %	37.000 - 41.000		
Mo %	0.500 max.		
Fe %	Balance	Mechanical Properties	
-	-	Tensile Strength in Mpa	450 - 470
-	-	Yield Strength in Mpa	240 - 270
-	-	Elongation in %	3.5 - 4
-	-	Reduction of Area in %	-
-	-	Hardness in HB	135 - 210
-	-	Impact in Joule	-
	C % Si % Mn % P % S % Cr % Ni % Mo % Fe % - - - - -	C % 0.350 - 0.750   Si % 2.500 max.   Mn % 2.000 max.   P % 0.050 max.   S % 0.050 max.   Cr % 17.000 - 21.000   Ni % 37.000 - 41.000   Mo % 0.500 max.   Fe % Balance   - -   - -   - -   - -   - -	C % 0.350 - 0.750   Si % 2.500 max.   Mn % 2.000 max.   P % 0.050 max.   S % 0.050 max.   Cr % 17.000 - 21.000   Ni % 37.000 - 41.000   Mo % 0.500 max.   Fe % Balance   - -

Cross Reference Table				
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry	
N08004	UNS	USA	Casting	
N08050	UNS	USA	Casting	
A608 Grade HT 50	ASTM	USA	Casting	
G X 40 NiCrSiNb 38-18	DIN	Germany	Casting	
1.4849	DIN	Germany	Casting	
N08005	UNS	USA	Casting	
A297 Grade HT	ASTM	USA	Casting	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## **ONE STOP SOLUTION FOR METAL PARTS**