GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 6603 X04Cr17Ni12Mo2Ti

Standard Specification for Stainless Steel Bars and Flats

Group - Ferrous Stainless Steel Alloys

Sub Group - IS 6603 X04Cr17Ni12Mo2Ti Stainless Steel Bars and Flats

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bars and Flats

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Nickel	Ni %	10.500 - 14.000
Chromium	Cr %	16.000 - 18.000
Molybdenum	Mo %	2.000 - 3.000
Titanium	Ti %	0.005 - 0.800
Sulphur	S %	0.030 max.
Phosphorus	P %	0.045 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Softening or Hardening + Tempering or As-Raw

Mechanical Properties	
Tensile Strength in Mpa	490 - 690
Yield Strength in Mpa	220 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in HB	192 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
6529 X04Cr17Ni12Mo2Ti	IS	India	Blooms, Billets and Slabs
1570 X04Cr17Ni12Mo2Ti	IS	India	Steel
6911 X04Cr17Ni12Mo2Ti	IS	India	Plate, Sheet and Strip
683-13 21	ISO	International	Steel
1654-5 1.4571	DIN	Germany	Steel
10028-7 1.4571	EN	European Union	Steel
A 49-244 X6CrNiMoTi17-12	AFNOR NF	France	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.