GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 6911 202 (X 10Cr18Mn9Ni5)

Standard Specification for Stainless Steel Plate, Sheet and Strip Specification

Group - Ferrous Stainless Steel Alloys

Sub Group - IS 6911 202 (X 10Cr18Mn9Ni5) Stainless Steel Plate, Sheet and Strip Specification

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.150 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	8.000 - 10.000
Nickel	Ni %	4.000 - 6.000
Chromium	Cr %	17.000 - 19.000
Molybdenum	Mo %	0.700 max.
Sulphur	S %	0.030 max.
Phosphorus	P %	0.045 max.
Titanium	Ti %	0.100 max.
Niobium	Nb %	0.200 max.
Copper	Cu %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	620 min.
Yield Strength in Mpa	310 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	217 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
AMS-QQ-S-763 202	AISI	USA	Steel
QQ-S-763 202	AMS	USA	Steel, Bars, Wire, Shapes and Forging
AMS-QQ-S-763 202	SAE	USA	Steel, Bars, Wire, Shapes and Forging
J 405 202	SAE	USA	Steel
1554 202 S 16	B.S.	United Kingdom	Steel and Wire
A 412 Type 202	ASTM	USA	Plate, Sheet and Strip
SA-213 TP202	ASME	USA	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.