GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 7899 Grade 4 Class B

Standard Specification for Alloy Steel Castings Suitable For Pressure Service-Specification

Group - Ferrous Mild Steel Alloys
Sub Group - IS 7899 Grade 4 Class B Alloy Steel Castings Suitable For Pressure Service-Specification
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition		
Carbon	C %	0.300 max.
Silicon	Si %	0.800 max.
Manganese	Mn %	1.000 max.
Sulphur	S %	0.045 max.
Phosphorus	P %	0.040 max.
Chromium	Cr %	0.400 - 0.800
Nickel	Ni %	0.400 - 0.800
Molybdenum	Mo %	0.150 - 0.300
Copper	Cu %	0.500 max.
Tungsten	W %	0.100 max.
Vanadium	V %	0.030 max.
Other	Ot %	0.600 max.
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment
Quenching or Tempering

Mechanical Properties	
Tensile Strength in Mpa	725 - 895
Yield Strength in Mpa	585 min.
Elongation in %	16 min.
Reduction of Area in %	35 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
G86150	UNS	USA	Steel
G86170	UNS	USA	Steel
G 4103 SNCM 220	JIS	Japan	Steel
G 3311 SNCM 220 M	JIS	Japan	Steel and Strip
1652-3 21 NiCrMo 2	DIN	Germany	Steel
1654-3 21 NiCrMo 2	DIN	Germany	Steel
1652-3 21 NiCrMoS 2	DIN	Germany	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.