

Material - ISO 1.3956

Standard Specification for Cast Steels and Alloys with Special Physical Properties

Group - Ferrous Stainless Steel Alloys

Sub Group - ISO 1.3956 Cast Steels and Alloys with Special Physical Properties

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------------|----------|
| Carbon | C % | 0.060 max. | Solution Annealing | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 4.000 - 6.000 | | |
| Phosphorus | Р% | 0.040 max. | | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 20.500 - 23.500 | | |
| Nickel | Ni % | 11.500 - 13.500 | | |
| Molybdenum | Mo % | 1.500 - 3.000 | | |
| Vanadium | V % | 0.100 - 0.300 | Mechanical Properties | |
| Niobium | Nb % | 0.100 - 0.300 | Tensile Strength in Mpa | 580 min. |
| Nitrogen | N % | 0.200 - 0.400 | Yield Strength in Mpa | 290 min. |
| Iron | Fe % | Balance | Elongation in % | 24 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| SA-351 Grade CG6MMN | ASME | USA | Casting | |
| A 743 CG6MMN | ASTM | USA | Casting | |
| A351 CG6MMN | ASTM | USA | Casting | |
| J93790 | UNS | USA | Casting | |
| GX4CrNiMnN22-12-5 | ISO | International | Casting | |
| CG6MMN | KS | Korea | Casting | |
| 5764 | SAE | USA | Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS