



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ISO 1083 | JS | 500-7 | S

Standard Specification For Spheroidal Graphite Cast Irons Castings

Group - Ferrous SG Iron | Ductile Iron Alloys

Sub Group - ISO 1083 | JS | 500-7 | S Spheroidal Graphite Cast Irons Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	-	As-Cast	
Silicon	Si %	-		
Manganese	Mn %	-		
Phosphorus	P %	-		
Sulphur	S %	-		
Chromium	Cr %	-		
Nickel	Ni %	-		
Copper	Cu %	-		
Iron	Fe %	-		
-	-	-		
Mechanical Properties			Tensile Strength in Mpa	500 min.
-	-	-	Yield Strength in Mpa	320 min.
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
JS 500-7	AS	Australia	Casting
EN-GJS-500-7	BS	British	Casting
EN-JS1050	UNE	Spain	Casting
5.3200	SS	Sweden	Casting
FCD 500-7	JIS	Japan	Casting
EN-JS1040	DIN	Germany	Casting
5.3200	EN	European Union	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS