



Material - ISO 11 CrMo 9-10

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - ISO 11 CrMo 9-10 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.150	Quenching + Tempering	
Silicon	Si %	0.150 - 0.400		
Manganese	Mn %	0.300 - 0.700		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.200		
Aluminium	Al %	0.020 max.		
Copper	Cu %	0.250 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 480 - 630 Yield Strength in Mpa 280 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-2	BS	British	Steel and Flat
1.7383	DIN	Germany	Steel and Flat
1.7383	DIN	Germany	Steel and Flat
11CrMo9-10	AFNOR NF	France	Steel and Flat
11CrMo9-10	BS	British	Steel and Flat
11CrMo9-10	UNI	Italy	Steel and Flat
11CrMo9-10	DIN	Germany	Steel and Flat

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.