



## Material - ISO GX4CrNiMnN22-12-5

Standard Specification for Cast Steels and Alloys with Special Physical Properties

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ISO GX4CrNiMnN22-12-5 Cast Steels and Alloys with Special Physical Properties Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	4.000 - 6.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	20.500 - 23.500		
Nickel	Ni %	11.500 - 13.500		
Molybdenum	Mo %	1.500 - 3.000		
Vanadium	V %	0.100 - 0.300	Mechanical Properties	
Niobium	Nb %	0.100 - 0.300	Tensile Strength in Mpa	580 min.
Nitrogen	N %	0.200 - 0.400	Yield Strength in Mpa	290 min.
Iron	Fe %	Balance	Elongation in %	24 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SA-351 Grade CG6MMN	ASME	USA	Casting	
A 743 CG6MMN	ASTM	USA	Casting	
A351 CG6MMN	ASTM	USA	Casting	
J93790	UNS	USA	Casting	
1.3956	ISO	International	Casting	
CG6MMN	KS	Korea	Casting	
5764	SAE	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.