



Material - JIS G 3539 SWRCH 19A

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging Group - Ferrous Mild Steel Alloys

Sub Group - JIS G 3539 SWRCH 19A Carbon Steel Wire Rods for Cold Heading and Cold Forging Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.200		
Silicon	Si %	0.100 max.	As Raw or Normalizing or Annealing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		aaling or Hardoning and
Phosphorus	P %	0.030 max.		•
Sulphur	S %	0.035 max.		
Aluminium	Al %	0.020 min.		
Iron	Fe %	Balance		
-	1	-		•
-	1	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	412 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRB	86 max.
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SWCH 19A	JIS	Japan	Wire Rod and Forging	
SWRCH19A	MS	Malaysia	Wire Rod and Forging	
SWRCH19A	KS	Korea	Wire Rod and Forging	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.