



Material - JIS SCH 24

Standard Specification for Heat-Resistant Cast Steels and Alloys for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - JIS SCH 24 Heat-Resistant Cast Steels and Alloys for General Applications
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 - 0.750	As - Cast	
Silicon	Si %	2.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	24.000 - 28.000		
Molybdenum	Mo %	0.500 max.		
Nickel	Ni %	33.000 - 37.000		•
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	440 min.
-	-	-	Yield Strength in Mpa	235 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4857	DIN	Germany	Casting	
G X 40 NiCrSi 35-25	DIN	Germany	Casting	
40 NiCrSi 35-25	MSZ	Hungary	Casting	
G X 50 NiCrSi 35-25	UNI	Italy	Casting	
N08705	UNS	USA	Casting	
A297 Grade HP	ASTM	USA	Casting	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.