



## Material - JIS SCPH 32-CF

## **Standard Specification for Steel Castings for Pressure Purposes**

**Group - Ferrous Mild Steel Alloys** 

Sub Group - JIS SCPH 32-CF Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.		
Silicon	Si %	0.600 max.	Normalizing or Quenching or Solution Annealing	
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	1.900 - 2.600		
Molybdenum	Mo %	0.900 - 1.200		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.	Mechanical Properties	
Tungsten	W %	0.100 max.	Tensile Strength in Mpa	410 min.
Iron	Fe %	Balance	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	19 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in HB	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
EN 10213 G17CrMo9-10	BS	British	Plate, Tubes and Forging	
G17CrMo9-10	ISO	International	Casting	
1.7379	ISO	International	Casting	
15 CD9.10-M	AFNOR NF	France	Pump, Valve and Fitting	
SCPH 32	JIS	Japan	Casting	
A 217 Grade WC9	ASTM	USA	Casting	
A 217 J21890	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.