



Material - JIS SCPH 32

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - JIS SCPH 32 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	2.000 - 2.750		
Molybdenum	Mo %	0.900 - 1.200		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.		
Tungsten	W %	0.100 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 480 min. Yield Strength in Mpa 275 min. Elongation in % 17 min. Reduction of Area in % 35 min. Hardness in HB - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17CrMo9-10	BS	British	Plate, Tubes and Forging
G17CrMo9-10	ISO	International	Casting
1.7379	ISO	International	Casting
15 CD9.10-M	AFNOR NF	France	Pump, Valve and Fitting
A 217 Grade WC9	ASTM	USA	Casting
A 217 J21890	ASTM	USA	Casting
SCPH 32-CF	JIS	Japan	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.