



## Material - JIS SCPL 1

### Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - JIS SCPL 1 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Tubes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	1.000 max.		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min
-	-	-	Yield Strength in Mpa	245 min.
-	-	-	Elongation in %	21 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 GP280GH	BS	British	Plate, Tubes and Forging
SCPH 2	JIS	Japan	Plate, Tubes and Forging
A 216 Grade WCC	ASTM	USA	Casting
GP 280 GH	DIN	Germany	Plate, Tubes and Forging
GP 280 GH	MSZ	Hungary	Plate, Tubes and Forging
GP 280 GH	UNI	Italy	Plate, Tubes and Forging
GP 280 GH	UNE	Spain	Plate, Tubes and Forging

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.