



## Material - JIS SCPL1

**Standard Specification for Steel Castings for Low Temperature and High Pressure Service**

**Group - Ferrous Mild Steel Alloys**

**Sub Group - JIS SCPL1 Steel Castings for Low Temperature and High Pressure Service**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Casting**

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.100 max.		
Nickel	Ni %	0.500 max.		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	245 min.
-	-	-	Elongation in %	21 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J03011	UNS	USA	Casting
1.1811	DIN	Germany	Casting
161-480	BS	British	Casting
1.5408	EN	European Union	Rod, Bars, Wire and Extrusion
1030	AISI	USA	Forging, Bar, Wire, and Shape
A732 2Q	ASTM	USA	Casting
A732 2A	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.