



Material - JIS SCW 480

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - JIS SCW 480 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 max.		
Silicon	Si %	0.800 max.	Normalizing or Quenching or Solution Annealing	
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	0.500 max.		
Iron	Fe %	Balance		•
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	480 min.
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	27 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
EN 10213 G17Mn5	BS	British	Plate, Tubes and Forging	
GS-16 Mn 5	DIN	Germany	Plate, Tubes and Forging	
SC 480	JIS	Japan	Casting	
SCW 490-CF	JIS	Japan	Casting	
G 17 Mn 5	MSZ	Hungary	Casting	
G 17 Mn 5	UNI	Italy	Casting	
G 17 Mn 5	UNE	Spain	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.