



Material - JIS SUH 309

Standard Specification for Iron-Chromium-Nickel, Bar, Wire, Rods, Sheets and Plat

Group - Ferrous Stainless Steel Alloys

Sub Group - JIS SUH 309 Iron-Chromium-Nickel, Bar, Wire, Rods, Sheets and Plat Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bar, Wire, Rods, Sheets and Plat

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.	Solution Annealing	
Phosphorus	P %	0.040 max.		nealing
Sulphur	S %	0.030 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	12.000 - 15.000		
Iron	Fe %	Balance		•
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	560 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	50 min
-	-	-	Hardness in BHN	201 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4833	EN	European Union	Hot or Cold Rolled, Sheet, Plate, Strip, Bar and Rods	
309	SAE	USA	Bar, Wire, Shapes and Forging	
X 16 CrNi 23-14	UNI	Italy	Plate, Sheet, Strip and Coil	
SA-351 Grade CH20	ASME	USA	Casting	
X 15 CrNi 24-13	AFNOR NF	France	Rolled Tubes for Pressure Service	
A743 CH20	ASTM	USA	Casting	
A351 CH20	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.