



Material - JIS SUS 316

Heat-Resisting Steel Plates and Sheets

Group - Ferrous Stainless Steel Alloys

Sub Group - G 4312 Heat-Resisting Steel Plates and Sheets

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Nickel	Ni %	10.000 - 14.000		
Molybdenum	Mo %	2.000 - 3.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 - 1470
-	-	-	Yield Strength in Mpa	205 - 548.1
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	187 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4409	DIN	Germany	Casting
1.4409	EN	European Union	Casting
316 S17	BS	British	Wire for Cold Forged Fasteners.
316	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging
03CH17N14M3	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging
A743 CF8M	ASTM	USA	Casting
A351 CF8M	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.