



Material - JIS SUS 420F

Standard Specification for Cold Finished Martensitic Stainless Steel Bars

Group - Ferrous Stainless Steel Alloys

Sub Group - JIS SUS 420F Cold Finished Martensitic Stainless Steel Bars

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.260 - 0.400		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.250 max.	Annealing or Hardening + Tempering	
Phosphorus	P %	0.060 max.		
Sulphur	S %	0.150 min.		
Chromium	Cr %	12.000 - 14.000		
Nickel	Ni %	0.600 max.		
Molybdenum	Mo %	0.600 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-		Tensile Strength in Mpa	590 - 930
-	-	-	Yield Strength in Mpa	540 min.
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	217 - 235
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
420F	AISI	USA	Bar, Wire, Shapes and Forging	
A895 Type 420F	ASTM	USA	Plate, Sheet and Strip	
A959 Type 420F	ASTM	USA	Bar, Wire, Shapes and Forging	
A 582 Type 420F	ASTM	USA	Bar and Forging	
J9154	UNS	USA	Casting	
S 42020	UNS	USA	Casting	
A743 CA40F	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.