



Material - JIS SUS 436L

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - JIS SUS 436L Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 19.000		
Molybdenum	Mo %	0.750 - 1.250		
Nickel	Ni %	0.600 max.	Mechanical Properties	
Titanium	Ti %	0.800 max.	Tensile Strength in Mpa	410 min.
Nitrogen	N %	0.025 max.	Yield Strength in Mpa	245 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	217 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S43600	ASTM	USA	Steel, Plate, Sheet and Strip
S43600	UNS	USA	Steel
436 S 20	BS	British	Steel and Wire
51436	SAE	USA	Steel
A959 Type 436	ASTM	USA	Steel
STS 436L	KS	Korea	Steel, Sheet, Plate and Strip
A651 TP 434	ASTM	USA	Steel and Tube

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.