

Material - KS D 3554 SWRM 6

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group - Ferrous Mild Steel Alloys

Sub Group - KS D 3554 SWRM 6 Carbon Steel Wire Rods for Cold Heading and Cold Forging Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As Raw or Normalizing or Annealing or Hardening and Tempering	
Manganese	Mn %	0.600 max.		
Phosphorus	Р%	0.040 max.		ling or Hardoning and
Sulphur	S %	0.040 max.		
Iron	Fe %	Balance		5
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	290 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	45 min.
-	-	-	Hardness in HRC	85 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
SWRCH 6R	JIS	Japan	Wire Rod and Forging	
SWCH 6R	JIS	Japan	Wire Rod and Forging	
SWRMF 6	KS	Korea	Wire Rod and Forging	
SWRCH6R	KS	Korea	Wire Rod and Forging	
SWRM 6	JIS	Japan	Wire Rod and Forging	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS