



## Material - KS D 3592 SWRCH6A

### Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group - Ferrous Mild Steel Alloys

Sub Group - KS D 3592 SWRCH6A Carbon Steel Wire Rods for Cold Heading and Cold Forging

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire Rod and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	As Raw or Normalizing or Annealing or Hardening and Tempering	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.600 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Aluminium	Al %	0.020 min.		
Chromium	Cr %	0.200 max.		
Copper	Cu %	0.300 max.		
Nickel	Ni %	0.200 max.		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      470 max. Yield Strength in Mpa      - Elongation in %      - Reduction of Area in %      66 min. Hardness in BHN      - Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SWRCH 6A	JIS	Japan	Wire Rod and Forging
SWCH 6A	JIS	Japan	Wire Rod and Forging
SWRCH6A	MS	Malaysia	Wire Rod and Forging
C2C	ISO	International	Wire Rod and Forging
C4C	ISO	International	Wire Rod and Forging
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.