GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - KS D 3698 STS304LN

Standard Specification for Cold-Rolled Stainless Steel Sheet and Strip

Group - Ferrous Stainless Steel Alloys

Sub Group - KS D 3698 STS304LN Cold-Rolled Stainless Steel Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Sheet and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Nickel	Ni %	8.500 - 11.500
Chromium	Cr %	17.000 - 19.000
Nitrogen	N %	0.120 - 0.220
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	550 min.
Yield Strength in Mpa	245 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in HB	217 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
G 4305 SUS 304 LN	JIS	Japan	Plate, Sheet and Strip
G 4304 SUS 304 LN	JIS	Japan	Plate, Sheet and Strip
G 4303 SUS 304 LN	JIS	Japan	Steel and Bars
9327-5 X 2 CrNiN 18 10	ISO	International	Steel and Bars
9329-4 X 2 CrNiN 18 10	ISO	International	Steel and Tubing
9330-6 X 2 CrNiN 18 10	ISO	International	Steel and Tubing
9328-5 X 2 CrNiN 18 10	ISO	International	Plate and Strips

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.