GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - KS D 3698 STS317L

Standard Specification for Cold-Rolled Stainless Steel Sheet and Strip

Group - Ferrous Stainless Steel Alloys

Sub Group - KS D 3698 STS317L Cold-Rolled Stainless Steel Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Sheet and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Nickel	Ni %	11.000 - 15.000
Chromium	Cr %	18.000 - 20.000
Molybdenum	Mo %	3.000 - 4.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	480 min.
Yield Strength in Mpa	175 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in HB	187 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J 405 317L	SAE	USA	Steel
J 405 317LN	SAE	USA	Steel
A 167 Type 317L	ASTM	USA	Plate, Sheet and Strip
A 167 Type 317LN	ASTM	USA	Plate, Sheet and Strip
A 182 F 317L	ASTM	USA	Steel and Pipe
A 240 Type 317L	ASTM	USA	Plate, Sheet and Strip
A 240 Type 317LN	ASTM	USA	Plate, Sheet and Strip

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.