



Material - KS STS 350

Standard Specification for Austenitic Chromium Nickel Molybdenum Nitrogen Stainless Steel

Group - Ferrous Stainless Steel Alloys

Sub Group - KS STS 350 Austenitic Chromium Nickel Molybdenum Nitrogen Stainless Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|------------------------------|----------|
| Carbon | C % | 0.030 max. | | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 1.500 max. | Solution Annealing | |
| Phosphorus | P % | 0.035 max. | | |
| Sulphur | S % | 0.020 max. | | |
| Chromium | Cr % | 22.000 - 24.000 | | |
| Nickel | Ni % | 20.000 - 23.000 | | |
| Molybdenum | Mo % | 6.000 - 6.8000 | | |
| Copper | Cu % | 0.400 max. | Mechanical Properties | |
| Nitrogen | N % | 0.210 - 0.320 | Tensile Strength in Mpa | 674 min. |
| Iron | Fe % | Balance | Yield Strength in Mpa | 330 min. |
| - | - | - | Elongation in % | 40 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardn <mark>ess in HB</mark> | 250 max. |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | | |
|-----------------------|----------|--------------------------------------|--|--|
| Material | Standard | Country Grade Belong to the Industry | | |
| A240 S 32050 | ASTM | USA | Plate, Sheet and Strip | |
| A358 S 32050 | ASTM | USA | Pipes | |
| A959 S 32050 | ASTM | USA | Plate, Sheet and Strip | |
| A249 S 32050 | ASTM | USA | Tubes for Superheater and Heat exchanger | |
| A213 S 32050 | ASTM | USA | Tubes for Superheater and Heat exchanger | |
| A743 CK35MN | ASTM | USA | Casting | |
| S 32050 | UNS | USA | Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.