

Material - KS STS 430

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - KS STS 430 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.		
Silicon	Si %	0.750 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	Annealing or Hardening + Tempering	
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Nickel	Ni %	0.600 max.		
Iron	Fe %	Balance		
-	1	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 - 780
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in HB	183 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S43000	ASTM	USA	Steel, Plate, Sheet and Strip		
430	AISI	USA	Steel		
430	AMS	USA	Sheet, Bar, Wire, Shape and Forging		
430	AS	Australia	Steel, Sheet, Plate and Strip		
430	SAE	USA	Sheet, Bar, Wire, Shape and Forging		
SUS 430	JIS	Japan	Steel, Wire and Bar		
A182 F 430	ASTM	USA	Steel, Pipe and Forging		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.