



Material - KS STS XM-27

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Group - Ferrous Stainless Steel Alloys

Sub Group - KS STS XM-27 Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.010 max.	Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.400 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	25.000 - 27.500		
Molybdenum	Mo %	0.750 - 1.500		
Nickel	Ni %	0.500 max.		
Nitrogen	N %	0.015 max.		
Copper	Cu %	0.200 max.		
Ni + Cu	Ni% + Cu%	0.500 max.	Mechanical Properties Tensile Strength in Mpa 410 min. Yield Strength in Mpa 245 min. Elongation in % 20 min. Reduction of Area in % 45 min. Hardness in HB 219 max. Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S44627	ASTM	USA	Steel, Plate, Sheet and Strip
S44627	UNS	USA	Steel
XM-27	SAE	USA	Steel
SUS SM-27	JIS	Japan	Steel and Bar
A276 XM-27	ASTM	USA	Steel, Bar and Shapes
A314 XM-27	ASTM	USA	Steel, Bar, Rolling and Forging
A182 F XM-27Cb	ASTM	USA	Steel, Pipe and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.