



Material - MS 1795 SWRCH15K

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group - Ferrous Mild Steel Alloys

Sub Group - MS 1795 SWRCH15K Carbon Steel Wire Rods for Cold Heading and Cold Forging

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire Rod and Forging

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|---|--|
| Carbon | C % | 0.130 - 0.180 | As Raw or Normalizing or Annealing or Hardening and Tempering | |
| Silicon | Si % | 0.100 - 0.350 | | |
| Manganese | Mn % | 0.300 - 0.600 | | |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.035 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | Mechanical Properties Tensile Strength in Mpa 370 min. Yield Strength in Mpa 260 min. Elongation in % 13 min. Reduction of Area in % 50 min. Hardness in BHN - Impact in Joule 30 J @ RT | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|---------------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| SWRCH 15K | JIS | Japan | Wire Rod and Forging |
| C15GC | ISO | International | Wire Rod and Forging |
| SWRCH15K | KS | Korea | Wire Rod and Forging |
| - | - | - | - |
| - | - | - | - |
| - | - | - | - |
| - | - | - | - |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.