



Material - MS 1795 SWRCH22A

Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

Group - Ferrous Mild Steel Alloys

Sub Group - MS 1795 SWRCH22A Carbon Steel Wire Rods for Cold Heading and Cold Forging Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire Rod and Forging

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|---|-------------------------|
| Carbon | C % | 0.180 - 0.230 | | |
| Silicon | Si % | 0.100 max. | As Raw or Normalizing or Annealing or Hardening and Tempering | |
| Manganese | Mn % | 0.700 - 1.000 | | oaling or Hardoning and |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.035 max. | | |
| Aluminium | Al % | 0.020 min. | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | Mechanical Properties | |
| - | - | | Tensile Strength in Mpa | 580 max. |
| - | - | | Yield Strength in Mpa | • |
| - | - | - | Elongation in % | • |
| - | - | - | Reduction of Area in % | 45 min. |
| - | - | - | Hardness in BHN | • |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| SWRCH 22A | JIS | Japan | Wire Rod and Forging | | |
| SWCH 22A | JIS | Japan | Wire Rod and Forging | | |
| C20C | ISO | International | Wire Rod and Forging | | |
| SWRCH22A | KS | Korea | Wire Rod and Forging | | |
| - | - | - | - | | |
| - | - | - | - | | |
| - | - | - | - | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.